

TONDINI PER CEMENTO ARMATO		
DIAMETRO NOMINALE (\emptyset)	PESO	SEZIONE
mm	Kg/ml	cmq
5	0.154	0.200
6	0.222	0.283
7	0.302	0.390
8	0.395	0.503
9	0.499	0.640
10	0.617	0.785
11	0.746	0.950
12	0.888	1.131
14	1.208	1.54
16	1.578	2.01
18	1.998	2.54
20	2.466	3.14
22	2.984	3.80
24	3.551	4.52
25	3.850	5.91
26	4.168	5.31
28	4.832	6.16
30	5.549	7.07
32	6.313	8.04